

Zinc-Nickel

SLOTOLLOY ZN 80 VX

Zinc-Nickel SLOTOLLOY ZN 80 VX is an alkaline process for the deposition of zinc-nickel coatings with 12 - 15 % by weight nickel in the alloy.

Zinc-Nickel SLOTOLLOY ZN 80 VX is operated with the Special Anode VX 1. It has a good metal distribution as well as a constant alloy composition over a wide current density range.

The process features by a significant reduced decomposition of the organic components and is registered for patent.

By the respective passivation of our SLOTOPAS series, blue, colourful iridescent, transparent and black conversion layers with a high corrosion protection can be produced. For a possible subsequent sealant the products of our SLOTOFIN series are available.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance only. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at www.schloetter.com/downloads.

For the storage of chemical products the TRGS 510 must be followed.

If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.

