

# Aluminium Pickle SLOTOCLEAN AK 60

Pickle Additive SLOTOCLEAN AK 61 is used as an additive in sodium hydroxide long-running pickle.

Pickle Additive SLOTOCLEAN AK 61 is a weak alkaline concentrate (approx. pH 9) and it is free from nitrate, nitride, chlorate and chloride. It has excellent wetting- and dispersing characters and contains specific organic oxidants and complexing agents to prevent the formation of scale even at high aluminium concentrations.

Pickle Additive SLOTOCLEAN AK 61 provides the achievement of equal E 6-surfaces on aluminium and its alloys.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

#### Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at [www.schloetter.com/downloads](http://www.schloetter.com/downloads).

For the storage of chemical products the TRGS 510 must be followed.

**If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.**

