

## Degreaser SLOTOCLEAN EL DCG

The Degreaser SLOTOCLEAN EL DCG is a universal cleaning process for electrolytic degreasing of steel, non-ferrous metals and zinc die cast.

Iron- or steel components are poled anodically although zinc die cast and non-ferrous metals are initially poled cathodically, pre-degreased and then are brief anodic pre-degreased. The anodic and cathodic treatment of non-ferrous metals and zinc die cast must be carried out in separate tanks.

Schlötter offers a wide range of additives to enhance cleaning. Please refer to technical data sheet BATH 02300-E Summary Degreaser Additives about the different possible combinations.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read this instruction carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at www.schloetter.com/downloads.

For the storage of chemical products the TRGS 510 must be followed.

If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.



Dr.-Ing. Max Schlötter GmbH & Co. KG Talgraben 30 73312 Geislingen/Steige Deutschland Page 1 of 1

T +49 (0) 7331-205-0 F +49 (0) 7331-205-123 <u>info@schloetter.de</u> www.schloetter.de



Certified Quality Company according to DIN EN ISO 9001: 2008 DIN EN ISO 14001: 2004 DIN EN ISO 50001: 2011