

Post-Dip Solution SLOTOPAS NT 1300

The Post-Dip Solution SLOTOPAS NT 1300 is used for post-treatment on already passivated zinc-nickel alloy layers. The Post-Dip Solution SLOTOPAS NT 1300 is applied alternatively to a sealant. It can be used for both rack- and barrel plating

Post-Dip Solution SLOTOPAS NT 1300 produces black passivated layers, less sensitive to touching, abrasion and scratches and ensures the necessary corrosion protection.

Transparent passivated zinc-nickel coatings treated with Post-Dip Solution SLOTOPAS NT 1300 become almost insensitive to fingerprints. This simplifies the handling of the parts enormously.

Post-Dip Solution SLOTOPAS NT 1300 is a purely inorganic post-treatment based on Cr(III) and contains neither Cr(VI) compounds nor cobalt.

The information in this data sheet is based on laboratory as well as practical experience. Figures quoted for operating limits and replenishment quantities are for guidance. Actual values necessary will depend on the components being plated (material and geometry), their application and plating plant conditions.

Important:

Please read this instructions carefully prior to the use of the process and carefully follow all the parameters that have a direct influence on the operation. We reserve the right to make technical changes. In the interest of safety, please pay attention to the hazard warnings on the labels of the containers. The minimum shelf life of the products is included on the labels and is also available in the appropriate Quality Assurance (QA03).

The current IMDS number of the layer deposited from the process is available on the internet at www.schloetter.com/downloads.

For the storage of chemical products the TRGS 510 must be followed.

If the additives used in this process contain a SVHC-substance, then this will be specified in the corresponding Material Safety Data Sheet, section 15.

